



Effective October 11, 2010

800RA

PLASTIC ADHESION PROMOTOR

Description

Transparent adhesion promotor for use on uncoated plastics.
Composition based on chlorinated polyolefine.

Products

800RA Plastic Adhesion Promotor - aerosol

Properties

- Gives excellent adhesion on exterior plastic car parts.
- VOC compliant, conform with directive 2004/42/EC.

Substrates

- Uncoated exterior plastic types as listed:
AAS, ABS, PBTP, PC, PP/EPDM, PVC, GRP.








Effective October 11, 2010

800RA

PLASTIC ADHESION PROMOTOR

PRODUCT PREPARATION

 Mixing ratio	Ready for use.
VOC	745 g/l
 Pot life at 20°C	Not applicable.
 Number of coats	1-2
	Shake before use.
 Flash time	5 min between coats. 10 min before topcoating.
DFT	5-10 μ
This data relates only to the material designated herein and does not apply to use in combination with any other material or any process. The data is not to be considered as a warranty or quality specification and we assume no liability in connection with its use.	



Effective October 11, 2010

800RA

PLASTIC ADHESION PROMOTOR

RECOMMENDED USE

Surface preparation

1. Preheat 30 min at 60°C.
2. Allow to cool.
3. Clean surface with water and soap. Rinse and dry.
4. Clean with a DuPont Refinish preparatory cleaner for plastics.
Wipe dry with a clean cloth.
5. Scuff sanding with sanding pad.
6. Remove all traces of sanding dust, blowing oil-free compressed air.
7. Optionally clean with a DuPont Refinish preparatory cleaner for plastics.
Wipe dry with a clean cloth.
8. Degrease with a correct DuPont Refinish final cleaner/degreaser.
9. Wipe and blow dry.

Product data

Directive 2004/42/EC: 2004/42/IIB(e) (840)745: The EU limit value for this product (product category: IIB(e)) in ready to use form is maximum 840 g/l of VOC. The VOC content of this product in ready to use form is maximum 745 g/l.

Products	Packages (ml)	Shelf life at 20°C (year)	Density (kg/l)
800RA	400	2	0.806



Effective October 11, 2010

800RA

PLASTIC ADHESION PROMOTOR

RECOMMENDED USE (con'd)

Remarks

- Pressurised container 800RA: protect from sunlight and do not expose to temperatures exceeding 50°C.
- Degrease AAS, ABS, PC and PVC with a correct DuPont Refinish final cleaner/degreaser. For PA, EP and PUR do not use 800RA. For PP and POM flame treatment is needed.
- Note that on plastic parts the use of 805R in DuPont Refinish 2K surfacers, DuPont Refinish 2K topcoats and DuPont Refinish 2K clears is strongly recommended.
- Optimum results with DuPont Refinish Waterborne Basecoats will be obtained if flash till flat between coats is respected.
- Material has to be at room temperature (18-25°C) before use.
- For more specific information, please contact your DuPont representative.

Safety

Consult Safety Data Sheet prior to use. Observe the precautionary notices displayed on the container.